



POLYPRIMER



DESCRIPTION

RestoFinish Polyprimer is a two component Polyester resin based Sealer Surfacers Primer. It is designed as an all inclusive coating for the use on a variety of substrates. Once sanded, it may be overcoated with a number of topcoats.




SURFACE PREPARATION

Surface must be clean, dry and free of oil, grease, wax, rust, dirt or any foreign matter. Use appropriate cleaning process or solvent for each substrate.

Bare Steel: Apply directly to clean abraded surface. Ensure surface is free from dust and blasting residue using an air gun and clean lint free cloth. Clean before application with RestoFinish Polyester Solvent or acetone.

Fibreglass: Sand with abrasive, minimum of 120 grit. Clean with RestoFinish Polyester Solvent or acetone before application.

Existing Finishers and Fillers: Ensure coatings are cured and dry. Sand with minimum 120 grit and ensure surface is free from dust using an air gun and clean lint free cloth.




MIXING

Mixing ratio is 100:2 by volume. This is equal to 2%.

Product	Volume	Weight
Polyprimer	1000mls	1330 grams
Polyprimer Hardener	20mls	20 grams

Can be reduced up to 10% with RestoFinish Polyester Solvent. Stir before use.



POT LIFE

Catalysed Polyprimer 20°C is one hour.

Use within temperature range 15°C - 30°C.



APPLICATION

1 medium coat, 10 minutes between coats. Maximum 4 coats.

One coat is equal to 75-100 microns.



GUN SETUP AND CLEANING

Fluid tip 1.8 - 2.0mm @ 25-35 PSI.

Clean equipment with RestoFinish Polyprimer Solvent or Acetone.



FINISHING

Can be sanded wet or dry.

After sanding, can be directly topcoated.

HEALTH AND SAFETY

FOR PROFESSIONAL USE ONLY. Full instructions must be read before use.

Please refer to RestoFinish Polyprimer – Part A Safety Data Sheets (SDS) and product labels for full Health and Safety details and product handling instructions.

IMPORTANT: This product contains hazardous materials and appropriate PPE (personal protective equipment) must always be used. This information is available from your local RestoFinish stockist or online at www.restofinish.com.au. RestoFinish negates any liability where the user does not wear the recommended PPE and where user does not follow instructions and make inquiries as to the suitability of the product for intended purpose.

IN AN EMERGENCY DIAL 000 (AUS) or 111 (NZ) POLICE OR FIRE BRIGADE

RESTOFINISH
A Division of Global Finish Pty Ltd
6/8 Stockyard Place, West Gosford NSW Australia 2250
Telephone: + 61 (2) 4321 0339
Facsimile: + 61 (2) 4321 0338
Email: info@restofinish.com.au
www.restofinish.com.au