



RUSGO

TECHNICAL DATA SHEET

Nov 2025.



DESCRIPTION

RestoFinish RusGo is a phosphoric acid based concentrate designed specifically to remove rust from mild steel on automotive restorations. RusGo will treat steel prior to organic coating.



APPLICATION

Note: Surface must be clean, dry and free of oil, grease, wax, dirt, foreign matter

Medium and Light Rust: Dilute with water (clean/de-mineralized) up to 1:10 and apply with either spray bottle, brush or saturated cloth. Allow 5 minutes for reaction. Agitate rust with red scourer pad while wet. Do not allow liquid to dry. Remove and neutralize by washing off with water (clean/de-mineralized) and wiping thoroughly with a clean, wet cloth. Repeat process with a new damp cloth. Use a third clean dry cloth to thoroughly dry surface. Blow entire surface down with clean dry air and use methylated spirits or RestoFinish Polyprimer Solvent on a clean cloth to thoroughly remove traces of water. Use RestoFinish Metal Cleaner as the final clean as per Technical Data Sheet (TDS).


Heavy Rust: May take multiple applications. Apply on steel undiluted, allow five (5) minutes for reaction to begin. Scrub with wire brush or red scourer pad. Repeat as required. Do not allow liquid to dry. Remove and neutralize by washing off with water (clean/de-mineralized) and wiping thoroughly with a clean, wet cloth. Repeat process with a new damp cloth. Use a third clean dry cloth to thoroughly dry surface. Blow entire surface down with clean dry air and use methylated spirits or RestoFinish Polyprimer Solvent on a clean cloth to thoroughly remove traces of water. Use RestoFinish Metal Cleaner as the final clean as per TDS.

Soaking: Smaller parts can be soaked for up to two (2) days (concentrated or diluted). Careful monitoring is essential. Remove parts every few hours to review. Remove and neutralize as per Heavy Rust directions above.



COATINGS (SPRAYING)

Once metal has been treated with RusGo, coat steel with RestoFinish Epoxycat as per TDS as soon as possible within three (3) hours. RestoFinish AfterBlast can be applied to maintain a temporary rust free surface as per TDS.



POT LIFE

Use once de-canned within one (1) hour. Dispose of unused product. Do not return to original container. Use within temperature range 15°C - 30°C.



HEALTH & SAFETY

Please refer to Safety Data Sheet (SDS).

Contains Phosphoric Acid. Eye and skin protection must be worn. Wash from skin immediately.

If Swallowed – DO NOT INDUCE VOMITING – give a glass of water. SEEK MEDICAL ATTENTION.

HEALTH AND SAFETY FOR PROFESSIONAL USE ONLY. Full instructions must be read before use. Please refer to RestoFinish RusGo Safety Data Sheets (SDS) and product labels for full Health and Safety details and product handling instructions. IMPORTANT: This product contains hazardous materials and appropriate PPE (personal protective equipment) must always be used.

Products are suitable for professional use only. The data on this sheet indicate typical values. As application variables are a major factor in product performance, this information should serve as a general guide only. The data included in this application are based on our present knowledge and experience. RestoFinish assumes no responsibility or liability for use of this information. UNLESS RESTOFINISH AGREES IN WRITING, RESTOFINISH ASSUMES NO WARRANTIES, EXPRESS OR IMPLIED, AND REPUDIATES ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR SUITABILITY FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. RESTOFINISH WILL NOT BE LIABLE FOR ANY INCIDENTAL, SPECIAL OR SIGNIFICANT DAMAGES. Your only remedy for any fault in this product is the replacement of the defective product, or a refund of the product purchase price, at our discretion. The latest version supersedes all preceding versions. You can obtain the most recent version from our website www.restofinish.com.au or directly from your sales agent. It is the responsibility of the beneficiary of our products to verify that any proprietary rights and existing laws and legislation are observed.

RestoFinish® (a division of Global Finish Pty Ltd). All rights reserved. v1125

IN AN EMERGENCY DIAL 000 (AUS) or 111 (NZ) POLICE OR FIRE BRIGADE

RESTOFINISH A Division of Global Finish Pty Ltd 6/8 Stockyard Place, West Gosford NSW Australia 2250

Telephone: + 61 (2) 4321 0339 Facsimile: + 61 (2) 4321 0338 Email: info@restofinish.com.au www.restofinish.com.au